

refine leather



250 / Cogn / Cognac

refine leather

Refine — Aniline Leather

Grain leather from European raw hides. The leather is dyed through, chrome tanned and produced without the use of PCP and CFC which can be damaging to the environment.

Thickness (mm)	1,0-1,2
Flexing Endurance	≥30.000 (IUP 20/EN ISO 5402)
Lightfastness (scale I-8)	3 (IUF 402/EN ISO 105-B02)
Rubbing Dry, 100 rubbings (scale I-5)	≥4 (EN ISO 11640)
Rubbing Wet, 20 rubbings (scale I-5)	≥4 (EN ISO 11640)
Rubbing Sweat, 20 rubbings (scale I-5)	≥4 (EN ISO 11640)
Tear Strenght (N/cm)	≥20 (IUP 40 / EN ISO 3377-1)
Fire Test	BS5852-Part 1, CAL TB 117



550 / Yelw / Yellow



565 / Oran / Orange



4009 / Red / Red




692 / Lgrn / Light Green



778 / Trks / Turkis



779 / Sble / Sea Blue



681 / Dkgn / Dark Green



7008 / Purp / Purple



Beig / Beige



197 / Crem / Cream



691 / Ston / Stone



258 / Noug / Nougat



551 / Wsky / Whisky



250 / Cogn / Cognac




229 / Chut / Chestnut



240 / Copp / Copper



4060 / Fusc / Fuchsia



329 / Dkbw / Dark Brown



854 / Ligy / Light Grey




855 / Grey / Grey



842 / Blck / Black

refine leather

easy
leather




200 / Slwe / Soul White

Easy — Semi-Aniline Leather

Lightly buffed natural grain leather designed and processed in Italy. The semi-aniline leather is dyed through, chrome tanned and finishing is with resins and pigments.


Thickness (mm)	1,2-1,4
Flexing Endurance, Dry	50.000 Cycles no damage (EN ISO 5402)
Lightfastness (scale I-8)	>=5 (EN ISO 105-B02)
Rubbing Dry, 500 rubbings (scale I-5)	>=4 (EN ISO 11640)
Rubbing Wet, 250 rubbings (scale I-5)	>=4 (EN ISO 11640)
Rubbing Sweat, 80 rubbings (scale I-5)	>=4 (EN ISO 11640, ISO 11641)
Tear Strength (N/cm)	>=20 (EN ISO 3377-1)
Fire Test	BS5852-Part 1, CAL TB 117




286 / Zinc / Zinc




253 / Peni / Penicilin




212 / Papy / Papyrus




200 / Slwe / Soul White




290 / Poin / Porcelain




201 / Ivry / Ivory




219 / Sand / Sand




220 / Dorm / Desertstorm




292 / Cfte / Caffelatte




297 / Moon / Mouton



213 / Buck / Buckskin




214 / Clay / Clay




215 / Avna / Avana




295 / Tan / Tan




221 / Lion / Lion




222 / Cinn / Cinnamon




223 / Cogn / Cognac



228 / Cott / Cotto




289 / Hnut / Hezelnut




229 / Ecur / Ecureil




399 / Brun / Braun



301 / Dash / Dash



285 / Marb / Marble



237 / Pill / Pill




225 / Coer / Coriander



238 / Fepr / Facepowder




239 / Fdet / Fond-de-Tein




283 / Engy / Energy




296 / Ligh / Light




249 / Ciqa / Ciquita




250 / Perg / Pergamena




287 / Lmgs / Lemon Grass




251 / Caca / Carioca




243 / Pech / Peach




244 / Suet / Sunset



246 / Claw / Claw




245 / Rong / Redorange




240 / Beia / Begonia




233 / Poty / Pot-Purrry




299 / Hena / Henna




241 / Blod / Blood




232 / Anqe / Antique




247 / Part / Parrot




248 / Siam / Siam




288 / Phbx / Phonebox




234 / Boay / Bombay



242 / Wine / Wine




235 / Ribs / Ribes



284 / Aube / Aubergine




218 / Dune / Dune




226 / Pory / Pottery




252 / Vono / Volcano



227 / Jaer / Jasper




398 / Hrse / Horse




300 / Crcu / Crocus




236 / Carr / Carrubo




216 / Anti / Antilop




224 / Acou / Acajou




217 / Peat / Peatmoos




231 / Chut / Chestnut



230 / Cico / Ciocco




298 / Root / Root




293 / Ebny / Ebony




263 / Seze / S.Breeze



294 / Lime / Lime



254 / Moud / Moud



255 / Teon / Terragon




256 / Aloe / Aloe




257 / Cage / Camouflage




258 / Brch / Birch




264 / Aqal / Aqua Azul




260 / Mdve / Maldiv




259 / Oxde / Oxide




265 / Line / Lichene




266 / Otta / Ottanio



267 / Blpl / Blue Petrol




261 / Cgrn / Cedar Green




262 / Botl / Bottle



268 / Poli / Polinesia



269 / Turq / Tourquoise




270 / Paci / Pacific




291 / Ocia / Oceania




274 / Indi / Indigo




275 / Deep / Deep




271 / Pler / Plaster



276 / Crce / Crushed Ice



272 / Mgfg / Morning Fog




277 / Npol / North Pole




278 / Sini / Santorine




273 / Slbd / Steel Bird




279 / Mati / Matisse




202 / Perl / Pearl




208 / Lamb / Lamb




205 / Cidr / Cinder




203 / Cent / Ciment




280 / Wist / Wisteria




281 / Milk / Milka



282 / Laer / Lavender




209 / Tlde / Turtledove




206 / Smke / Smoke




204 / Iron / Iron




304 / Grey / Grey



210 / Grst / Greystone



211 / Grsw / Grayshadow



207 / Bick / Black

grace leather




21004 / Caml / Camel

Grace — Aniline Leather

Aniline leather from European raw hides with a natural look and velvety feel, characterized by the natural markings and imperfections that give it a distinct beauty. The leather is dyed through, tanned without chrome and produced without the use of PCP and CFC which can be damaging to the environment.

Thickness (mm)	1,1-1,3
Flexing Endurance	20.000 (EN ISO 5402-1)
Lightfastness (scale I-8)	≥3 (EN ISO 105-B02)
Rubbing Dry, 50 rubbings (scale I-5)	≥3 (EN ISO 11640)
Rubbing Wet, 20 rubbings (scale I-5)	≥3 (EN ISO 11640)
Rubbing Sweat, 20 rubbings (scale I-5)	≥3 (EN ISO 11640)
Tear Strenght (N/cm)	≥20 (EN ISO 3377-1/2)
Fire Test	BS5852-Part 1, CAL TB 117


grace leather




21003 / Anth / Anthrazite



21007 / Grey / Grey




21005 / Rgrn / Racing Green



21001 / Dkbw / Dark Brown




21002 / Rust / Rust




21004 / Caml / Camel




21000 / Cogn / Cognac



21008 / Ecru / Ecru



21009 / Alnd / Almond



21010 / Ston / Stone

grace leather

endure
leather




33004 / Cogn / Cognac

endure leather


Endure — Semi-Aniline Leather

Semi-aniline leather with high durability, making it ideal for contract environments. Leather from scandinavian raw hides. The leather is dyed through using a chrome free tanning process.


Thickness (mm)	1,1-1,3
Lightfastness (scale I-8)	6 (EN ISO 105-B02)
Rubbing Dry, 2000 rubbings (scale I-5)	4 (EN ISO 11640)
Rubbing Wet, 80 rubbings (scale I-5)	4 (EN ISO 11640)
Rubbing Sweat, 50 rubbings (scale I-5)	4 (EN ISO 11640)
Tear Strength (N/cm)	20 (DIN 53329)
Fire Test	BS5852-Part 1, CAL TB 117




00109 / Whit / White



00100 / Cwit / Cold White



00118 / Wwit / Warm White




01085 / Pegy / Pale Grey


endure leather




01037 / Mtgr / Mist Grey




11033 / Stgy / Soft Grey




11049 / Grey / Grey




11073 / Ligy / Light Grey




01043 / Clgy / Cool Grey




11152 / Segy / Sabre Grey




71017 / Dkgy / Dark Grey




11056 / Ccgy / Charcoal Grey




91102 / Anth / Antracit




93068 / Anbk / Antracit Black




99999 / Bick / Black




98087 / Dkak / Dark Khaki




01061 / Lupe / Light Taupe




13072 / Grge / Greige




13087 / Dkkg / Dark Greige



13048 / Stgr / Stone Grey




01021 / Ltgr / Light Greige




01003 / Kaki / Khaki




02122 / Ywgg / Yellow Greige




02119 / Stge / Soft Greige



93099 / Brwn / Brown




93129 / Dkbw / Dark Brown




93109 / Dcly / Dark Clay




33077 / Libw / Light Brown



33001 / Buur / Burnt Umber



43283 / Ochr / Ochre




33004 / Cogn / Cognac




54035 / Brnd / Brandy


endure leather




43054 / Clay / Clay




22030 / Sand / Sand



22024 / Beig / Beige




97038 / Bkbl / Black Blue




77127 / Dkbl / Dark Blue




77074 / Rlbe / Royal Blue




77237 / Dmbe / Denim Blue




77158 / Nabl / Navy Blue




07006 / Slbl / Steel Blue




17027 / Grbl / Grey Blue




87021 / Begn / Blue Green



78023 / Emdl / Emerald




08057 / Mint / Mint




08124 / Jgrn / Jade Green




88019 / Gren / Green




98015 / Dkgn / Dark Green




08055 / Sagn / Sage Green




08021 / Dgrn / Dusty Green




98047 / Olive / Olive



08038 / Bgrn / Beige Green




75014 / Purp / Purple




75010 / Plym / Plym



16377 / Lpup / Light Purple



16003 / Laer / Lavender



95006 / Dkby / Dark Burgundy



66006 / Mauv / Mauve




05029 / Ared / Amber Red




54021 / Taca / Terracotta

endure leather



45035 / Bred / Burnt Red




35126 / Dkrd / Dark Red




75011 / Cred / Carmine Red




05145 / Pink / Pink




55002 / Redv / Red Velvet



05011 / Red / Red



46053 / Tros / Tan Rose



45065 / Dkog / Dark Orange




54033 / Onge / Orange



44012 / Dkye / Dark Yellow


Be aware that the tones of digital color cards can vary from device to device. We suggest that you review a physical color sample of your selected color prior to proceeding with your order.

allure leather




30230 / Mtgr / Mist Grey


allure leather




30236 / Chal / Charcoal



30241 / Dkbw / Dark Brown




30237 / Mink / Mink




30238 / Cdar / Cedar

allure leather




30231 / Laer / Lavender




30230 / Mtgr / Mist Grey




30235 / Jade / Jade



30239 / Gold / Gold



30234 / Corl / Coral



30232 / Mon / Moon



30240 / Ivry / Ivory

Allure — Aniline Leather

Soft nubuck aniline leather from European raw hides, known for its exclusive appeal and soft, velvety feel. The leather is dyed through, chrome tanned and produced without the use of PCP and CFC which can be damaging to the environment.

Thickness (mm)	1,1-1,3
Lightfastness (scale I-8)	≥2-3 (EN ISO 105-B02)
Rubbing Dry, 50 rubbings (scale I-5)	≥3 (EN ISO 11640)
Rubbing Wet, 20 rubbings (scale I-5)	≥3 (EN ISO 11640)
Rubbing Sweat, 20 rubbings (scale I-5)	≥3 (EN ISO 11640)
Tear Strength (N/cm)	≥20 (EN ISO 3377)
Fire Test	BS5852-Part 1, CAL TB 117

Be aware that the tones of digital color cards can vary from device to device. We suggest that you review a physical color sample of your selected color prior to proceeding with your order.

illusion leather



44388 / Dkca / Dark Camel


Illusion

Illusion - Imitation leather


Imitation leather from PU (Polyurethane) is hard-wearing and easy to maintain which makes it particularly well suited to public spaces, such as restaurants, cafés and lounges. Imitation leather is also a good option for healthcare settings and public spaces where furniture and fittings require frequent and thorough cleaning.

Thickness (mm)	1 +/-0,1
Martindale	500.000 (EN ISO 5470-2)
Flexing Endurance	50.000 (EN ISO 5402-1)
Lightfastness (scale 1-8)	≥7 (EN ISO 105-B02)
Rubbing Dry (scale 1-5)	4-5 (EN ISO 105-X12)
Rubbing Wet (scale 1-5)	4-5 (EN ISO 105-X12)
Tensile Strength Warp (N/cm)	506/5 (ISO 1421)
Tensile Strength Weft (N/cm)	347/5 (ISO 1421)
Tear Strength Weft (N)	58 (ISO 4674-1)
Tear Strength Warp (N)	56 (ISO 4674-1)
Seam Slippage Warp (N)	200 (ISO 13936-1)
Seam Slippage Weft (N)	200 (ISO 13936-1)
Adhesion - Surface Finish Warp (N/cm)	35,8/5 (ISO 2411)
Adhesion - Surface Finish Weft (N/cm)	28,9/5 (ISO 2411)
Cold Cracking Resistance (°C)	-40 (EN 1876-1)
Tropical Rest (weeks)	10 (ISO 1419)
Fire Test	BS 5852 Crib 5, Cal TB 117, DIN 4102 B2, EN 1021-1 & 2, IMO 2010 FTP Code Part 8

Be aware that the tones of digital color cards can vary from device to device. We suggest that you review a physical color sample of your selected color prior to proceeding with your order.



00110 / Blck / Black



68746 / Blue / Blue



47124 / Cbou / Caribou



48013 / Choc / Chocolat




63174 / Ciel / Ciel



44388 / Dkca / Dark Camel



77773 / Dkgn / Dark Green



57841 / Grey / Grey




57069 / Ligy / Light Grey




66745 / Mrne / Marine




46508 / Mink / Mink



76725 / Petr / Petrol



58290 / Ston / Stone



87241 / Taup / Taupe



67382 / Tile / Tile

Illusion