

Resinex™ MX-2

Mixed bed ion exchange resin

Resinex™ MX-2 is a ready-to-use regenerable mixed bed resin specially designed for the production of fully demineralised water. The product is made up of a 1:1,5 volumetric ratio of **Resinex™ K-8** and **Resinex™ A-4** to offer a very low conductivity in the outlet during operation. The high operating capacity offers an economic advantage and the type 1 functional group in the anionic compound guarantees a high purity, silica free water.

Typical Properties

Type	Crosslinked polystyrene divinylbenzene
Form	gel-type, amber, spherical beads
Functional group	Sulfonic acid/Quarternary ammonium, Type 1
Whole bead count	95% min.
Ionic form, as shipped	H ⁺ /OH ⁻
Bead size	0.42 - 1.25 mm
Uniformity coefficient	1.60 max.
Bulk density, as shipped	740 kg/m ³
Water retention	45 - 55%
Operating capacity	Cation: 0.85 eq/l, Anion: 0.65 eq/l min.
Volume change regenerated -> exhausted	15% max.
Stability, pH	0 - 14

Key Features and Benefits

- **High Integrity Beads**
Excellent resistance to mechanical degradation ensures low pressure drop
- **High Operating Capacity**
Economical advantage
- **Low Conductivity Leakage**
Offers conductivity leakage <0.1 µS/cm and it is usable for all standard mixed bed applications.

Typical Applications

- Polishing after demineralisation
- Demineralisation in laboratories
- Mixed bed cartridges

Standard Packaging

- 25 lit. PE valve bag
- 1000 litre big bag

Standard Design Conditions

Bed depth	> 600 mm
Service flow rate	8 - 40 BV/h



TRADEMARK OF JACOBI CARBONS. WWW.JACOBI.NET


Resinex™

Ion Exchange Resin

Resinex™ MX-2

Mixed bed ion exchange resin

Pressure Drop



Product Packing



25 lit. polyethylene valve bag
48 bags per pallet



Polypropylene FIBCs
(big bag), 1.000 lit.



NOTICE Jacobi Carbons reserves the right to change product specifications without prior notification. The information contained in this datasheet is intended to assist a customer in the evaluation and selection of products supplied by Jacobi Carbons. The customer is responsible for determining whether products and the information contained in this document are appropriate for the customer's use. Jacobi Carbons assumes no obligation or liability for the usage of the information in this datasheet, no guarantees or warranties, expressed or implied, are provided. Jacobi Carbons disclaims responsibility and the user must accept full responsibility for performance of systems based on this data.

CAUTION Strong oxidizing agents such as nitric acid can react violently with ion exchange resins and cause explosive type reactions. Before using strong oxidants, consult sources knowledgeable in the handling of these materials.



SWEDEN

Jacobi Carbons AB
Vanvsholmen
SE-392 30 Kalmar
Phone: +46-480-417550
FAX: +46-480-417559
Email: info@jacobi.net

FINLAND

Jacobi Carbons AB (SS)
Ruoholahdenkatu 8
SF-00180 Helsinki
Phone: +358-9-643602
FAX: +358-9-642900
Email: infofin@jacobi.net

GERMANY

Jacobi Carbons GmbH
Feldbergstraße 21
D-60323 Frankfurt/Main
Phone: +49-69-719107-0
FAX: +49-69-719107-20
Email: infode@jacobi.net

UNITED STATES

Jacobi Carbons, Inc.
1518 Walnut Street, 10th Floor
Philadelphia, PA 19102
Phone: +1-215-546-3900
FAX: +1-215-546-9921
Email: infous@jacobi.net

UNITED KINGDOM

Jacobi Carbons Ltd
E12 Croft Court, Moss Estate
WN73PT Leigh, Lancashire
Phone: +44-1942-670600
FAX: +44-1942-670605
Email: infouk@jacobi.net

MALAYSIA

Jacobi Carbons (Asia) Sdn Bhd
Lot 12070-F, Jalan Usahajaya,
Permatang Tinggi, 14100, Penang
Phone: +60-4-5882122
FAX: +60-4-5886122
Email: infoasia@jacobi.net



Jacobi

www.jacobi.net

WORLDWIDE DISTRIBUTORS A diverse network of agents, strategically located around the world

Resinex and Jacobi are trademarks of Jacobi Carbons. © Jacobi Carbons AB, 2009

FX-MX2-A-E-20090907