

# mont marte

international PTY LTD

## LIGHTFASTNESS RATINGS

At Mont Marte we test our pigment based artists materials for Lightfastness rating using the British system - the Blue Wool Standard. There is also a US system for determining lightfastness - ASTM D4303-03 and below is a comparison Table of the two.

Blue Wool 7 - 8	Equivalent to ASTM I  Excellent Lightfastness  Under conditions of Museum exposure the pigment will remain unchanged for more than 100 years.
Blue Wool 6	Equivalent to ASTM II  Very Good Lightfastness  Under conditions of Museum exposure the pigment will remain unchanged for 50-100 years.
Blue Wool 4-5	Equivalent to ASTM III  Fair Lightfastness  Under conditions for Museum exposure the pigment will remain unchanged for 15-50 years.

*mont marte*

*Let's Paint.*

*mont marte*  
**creative kids**

*mont marte*  
**j-design**

*mont marte*  
**kids colour**



中华人民共和国扬州进出口玩具检验所  
YANGZHOU IMP. & EXP. TOY INSPECTION INSTITUTE OF P.R.C.

Add: 6 Kaifa West Road(225009), Yangzhou, Jiangsu, China  
TEL: +86(0)514-87885904 FAX: +86(0)514-87885882 E-mail: ytii@ytii.com http://www.ytii.com



ORIGINAL

## TEST REPORT

No : 3210/FA100346  
Date : Jan.30,2011

Applicant : TIANCHANG MONTMARTE INTERNATIONAL TRADING CO., LTD  
Address : Chuantang Village, Zhengji Town, Tianchang City, Anhui, Province, China  
Sample Description : Forty-eight sets of samples submitted by the applicant said to be  
(Photo Appendix is Included) 48 Colour Paint, Coating Thickness 100µM  
Item No. : PMDA0001-0048  
Place of Origin : China  
Date of Sample Received : Dec.06, 2010  
Testing Period : Jan.21,2011  
Test Requested : Colour Fastness To Light [ISO 105-B02:1994]  
Test Method : ISO 105 B02 : 1994  
Result : Please see the following page

Signed for and on behalf of YTII



  
Li Jing  
Quality Manager

Page: 1 of 3

The issuance of this report does not exonerate buyers or sellers from exercising all their rights and discharging all their liabilities under the Contract of Sale. Except by special arrangement, the test items will not be retained by the Company for more than three months. The results shown in this test report refer only to the sample(s) tested unless otherwise stated.

The test report cannot be reproduced except in full, without prior written permission of the Company

YTHW 0024815



ORIGINAL

## TEST REPORT

No : 3210/FA100346

Date : Jan.30,2011

### Test Group:

Group 01 : Titanium White Paint  
Group 02 : Zinc White Paint  
Group 03 : Cream Paint  
Group 04 : Naples Yellow Paint  
Group 05 : Lemon Yellow Paint  
Group 06 : Medium Yellow Paint  
Group 07 : Flesh Tint Paint  
Group 08 : Orange Paint  
Group 09 : Azo Vermillion Paint  
Group 10 : Brilliant Red Paint  
Group 11 : Permanent Red Paint  
Group 12 : Carmine Paint  
Group 13 : Magenta Paint  
Group 14 : Rose Madder Paint  
Group 15 : Mauve Paint  
Group 16 : Purple Paint  
Group 17 : Violet Paint  
Group 18 : Yellow Deep Paint  
Group 19 : Ultramarine Blue Paint  
Group 20 : Phthalo Blue Paint  
Group 21 : Cyan Blue Paint  
Group 22 : Cobalt Blue Paint  
Group 23 : Monastral Cerulean Paint  
Group 24 : Turquoise Paint

Group 25 : Viridian Paint  
Group 26 : Emerald Green Paint  
Group 27 : Monastral Green Paint  
Group 28 : Terre Verte Paint  
Group 29 : Sap Green Paint  
Group 30 : Hookers Green Deep Paint  
Group 31 : Olive Green Paint  
Group 32 : Raw Sienna Paint  
Group 33 : Yellow Ochre Paint  
Group 34 : Burnt Sienna Paint  
Group 35 : Red Ochre Paint  
Group 36 : Burnt Umber Paint  
Group 37 : Raw Umber Paint  
Group 38 : Vandyk Brown Paint  
Group 39 : Neutral Grey Paint  
Group 40 : Paynes Grey Paint  
Group 41 : Lamp Black Paint  
Group 42 : Gold Paint  
Group 43 : Silver Paint  
Group 44 : Pearl White Paint  
Group 46 : Pearl Wine Red Paint  
Group 47 : Pearl Purple Paint  
Group 48 : Pearl Sapphire Paint

### Test Result :

	(01)	(02)	(03)	(04)	(05)
Colour fastness to light(grade)	8	7	8	8	8
	(06)	(07)	(08)	(09)	(10)
Colour fastness to light(grade)	7	8	7	8	8
	(11)	(12)	(13)	(14)	(15)
Colour fastness to light(grade)	7	8	7	8	8
	(16)	(17)	(18)	(19)	(20)
Colour fastness to light(grade)	8	8	8	7	8

Page: 2 of 3

The issuance of this report does not exonerate buyers or sellers from exercising all their rights and discharging all their liabilities under the Contract of Sale Except by special arrangement, the test items will not be retained by the Company for more than three months. The results shown in this test report refer only to the sample(s) tested unless otherwise stated.

The test report cannot be reproduced except in full, without prior written permission of the Company

YTIWA 0058347





ORIGINAL

## TEST REPORT

No :3210/FA100346

Date :Jan.30,2011

	(21)	(22)	(23)	(24)	(25)
Colour fastness to light(grade)	8	8	8	8	8
	(26)	(27)	(28)	(29)	(30)
Colour fastness to light(grade)	7	6	7	7	7
	(31)	(32)	(33)	(34)	(35)
Colour fastness to light(grade)	6	8	8	8	8
	(36)	(37)	(38)	(39)	(40)
Colour fastness to light(grade)	8	8	8	8	8
	(41)	(42)	(43)	(44)	
Colour fastness to light(grade)	8	8	8	8	
	(46)	(47)	(48)		
Colour fastness to light(grade)	8	8	8		

Remarks: Accordance with customer requirements, blue wool reference grade 6 continue exposure until grey scale grade 4.

\*\*\*\*\*

\*\*\* End of Report \*\*\*

Page: 3 of 3

The issuance of this report does not exonerate buyers or sellers from exercising all their rights and discharging all their liabilities under the Contract of Sale. Except by special arrangement, the test items will not be retained by the Company for more than three months. The results shown in this test report refer only to the sample(s) tested unless otherwise stated.

The test report cannot be reproduced except in full, without prior written permission of the Company.

YTHWA 0058348




ORIGINAL

## APPENDIX

No :3210/FA100346

Date Jan.30,2011



YTII authenticates the photo on ORIGINAL report only.

Page:2 OF 8

The issuance of this report does not exonerate buyers or sellers from exercising all their rights and discharging all their liabilities under the Contract of Sale. Except by special arrangement, the test items will not be retained by the Company for more than three months. The results shown in this test report refer only to the sample(s) tested unless otherwise stated.

The test report cannot be reproduced except in full, without prior written permission of the Company.

YTHWA 0054823





中华人民共和国扬州进出口玩具检验所  
YANGZHOU IMP. & EXP. TOY INSPECTION INSTITUTE OF P.R.C.

Add: 6 Kaifa West Road(225009), Yangzhou, Jiangsu, China  
TEL:+86(0)514-87885904 FAX:+86(0)514-87885882 E-mail:ytii@ytii.com http://www.ytii.com




ORIGINAL

APPENDIX

No :3210/FA100346

Date Jan.30,2011



YTII authenticates the photo on ORIGINAL report only.

The issuance of this report does not exonerate buyers or sellers from exercising all their rights and discharging all their liabilities under the Contract of Sale. Except by special arrangement, the test items will not be retained by the Company for more than three months. The results shown in this test report refer only to the sample(s) tested unless otherwise stated.

The test report cannot be reproduced except in full, without prior written permission of the Company.




ORIGINAL

# APPENDIX

No :3210/FA100346

Date Jan.30,2011



YTII authenticates the photo on ORIGINAL report only.






ORIGINAL

# APPENDIX

No :3210/FA100346  
 Date Jan.30,2011



YTII authenticates the photo on ORIGINAL report only.




ORIGINAL

# APPENDIX

No :3210/FA100346

Date Jan.30,2011



YTII authenticates the photo on ORIGINAL report only.




ORIGINAL

# APPENDIX

No :3210/FA100346

Date Jan.30,2011



YTI authenticates the photo on ORIGINAL report only.






ORIGINAL

# APPENDIX

No :3210/FA100346

Date Jan.30,2011



YTII authenticates the photo on ORIGINAL report only.