

Use: Light Commercial / Residential flooring installations. Suitable for all living areas as well as for commercial areas with normal wear, (offices, waiting rooms, boutiques, etc.). The flooring is not suitable for installation in humid rooms (bathrooms, saunas, etc.).
Suitable for hot-water underfloor heating or electrical floor heating systems provided the flooring surface temperature doesn't exceed 80 °F (26 °C).
Nydree Maverick can also be floated on walls either horizontally or vertically. 5G Climb installation clips are needed.

Recommended Installation:

Floating installation, Välinge 5G® Locking System using Maverick Underlayment
Maverick Underlayment material: OmniChoice 1.4mm Acoustical Underlayment (Up to 3 lbs. Calcium Chloride Test)
OmniChoice w/Vapor Bloc Underlayment. (Up to 10 lbs. Calcium Chloride Test or up to 90% insitu-RH)
Use Foam with CS > 60 kPa & CC > 20 kPa. (According to EN 16354)
Maverick may also be glued down using Nydree SB1587 adhesive.

Construction/Species:

Wear Layer: 0.6mm (0.024") Sliced European White Oak, Walnut and Ash.
Moisture Resistant Composite Core, Backing Layer: Birch Veneer, Micro-beveled Edges.
Thickness Swell: EN 13329 / ISO 24336: <10%

Dimensions:

| | | |
|--------------------------------------|----------------------------|-------------------------|
| Width: 8.11" (206mm) | Thickness: 0.445" (11.3mm) | Length: 86.61" (2200mm) |
| Width: 5.94" (151mm) | Thickness: 0.362" (9.2mm) | Length: 46.06" (1170mm) |
| Maverick Herringbone (A or B plank): | | |
| Width: 3.58" (91mm) | Thickness: 0.445" (11.3mm) | Length: 21.5" (546mm) |

Hardness:

Resin reinforced wear layer. Resists dents and wear marks. Extreme impact resistance.
Modified Rockwell hardness: 85 to 105. Corresponding Janka Range: 5917 to 7357.
Brinell hardness: EN 1534. Result – 8 HB (average value)
Impact resistance: EN 14354:2017. Result – EC3

Colors: 8.11" Wide

White Oak: Keswick, Vienna, Ivy, Richmond, Bridgewater, Roanoke
Walnut: Arlington, Lynchburg
Ash: Waynesboro, Lexington

5.94" Wide

White Oak: Keswick, Vienna, Bridgewater, Arlington, Waynesboro

3.58" Wide Herringbone

White Oak: Keswick, Vienna, Bridgewater, Arlington

Finish / Gloss:

Standard UV-Cured finish. Deep matte finish. Gloss level (60°) is 3-5.
Taber Abrasion Resistance. EN 13329 Annex E (sandpaper method) – 650 cycles.
EN 14354 Annex D (Top Layer <1.0mm): >6000 cycles.

Effect of Household Chemicals on the Finish (ASTM D1308-02): 16 hour exposure and then cleaned with Bona Professional Hardwood Floor Cleaner.

All of the following chemicals showed no visible change:

| <u>Refrigerator</u> | <u>Medical/Cleaning</u> | <u>Chemicals</u> | <u>Misc.</u> |
|---------------------|--|----------------------|------------------|
| Cold Water | Ethyl Alcohol | Acetone | Lighter Fluid |
| Hot Water | (Hand Sanitizer & Alcohol Wipes) | 10% Sodium Hydroxide | 10W-30 Motor Oil |
| Vinegar | Undiluted Bleach | 30% Sulfuric Acid | |
| Red Grape Juice | Lysol | | |
| Olive Oil | Undiluted Ammonia | | |
| Ketchup | 3M Neutral Quat Disinfectant (0.5 oz./gal) | | |
| Coffee | 3M HB Quat Disinfectant (0.35 oz./gal) | | |
| Tea | Hydrogen Peroxide | | |
| Cocoa | Super Shine-All APC | | |
| Coke | 1% Dawn Dish in Water | | |
| Orange Juice | 1% Ivory Bar Soap in Water | | |

The only reagent that showed a slight stain was Mustard.

Acoustic Properties (ASTM E90 and E492):

| Subfloor | Flooring System | Ceiling | STC | IIC |
|-------------|--|-------------------|-----|-----|
| 8" Concrete | Nydree Maverick Flooring with Underlayment | None | 55 | 55 |
| 8" Concrete | Nydree Maverick Flooring with Underlayment | Insulated Ceiling | 63 | 68 |

Fire: EN 13501. Result – Bfl-S1 (Hardly flammable)
 ASTM E648. Average Critical Radiant Flux (CRF) = 0.82 watts/cm². Class I.
 ASTM E662. Smoke Density: 316 Flaming / 255 Non-Flaming.
 ASTM E84. Class C.

Slip Resistance (ANSI A137.1): 0.73 'Wet'

Thermal Conductivity:

ASTM C518. Result – 0.1799 W/(m•K) or 1.2472 BTU•in/(hr•ft²•°F)

Thermal Resistance:

EN 12664 / 12667: R 0.07 (m² x K)/W

Environmental / LEED Info:

Formaldehyde Emission. EN 717-1. Result – E1 (CARB2 Compliant).

Warranty:

Residential Limited Lifetime - Structural Defects, Topical Spills (<24 hrs.) and Wear Through of Top Veneer Layer.
 Light Commercial / Hotel Guest Rooms – 10 Year - Structural Defects, Topical Spills (<24 hrs.) and Wear Through of Top Veneer Layer.

See Maverick Warranty for complete details.

Care & Maintenance:

Periodically clean with Bona® Professional Hardwood Floor Cleaner.

Recoating: The Bona Prep® recoating system is recommended. System is Greenguard Certified.

Accessories: See Maverick Accessories Bulletin. All accessories are manufactured and finished by Nydree Flooring.

Packaging:

| | |
|---------------------------------|-----------------------------|
| Width x Length | 8.11" x 86.61" |
| Boards / box | 4 |
| Square Feet / box | 19.51 |
| Square Feet / pallet (48 boxes) | 937 |
| Weight / box (lbs.) | 44.3 |
| 20' Container Quantity | 18 pallets / 16,866 sq. ft. |

| | |
|---------------------------------|-------------------------------|
| Width x Length | 5.94" x 46.06" |
| Boards / box | 9 |
| Square Feet / box | 17.10 |
| Square Feet / pallet (35 boxes) | 598.5 |
| Weight / box (lbs.) | 31.6 |
| 20' Container Quantity | 33 pallets / 19,750.5 sq. ft. |
| 40' Container Quantity | 39 pallets / 23,341.5 sq. ft. |

| | |
|---------------------------------|---------------|
| Width x Length | 3.58" x 21.5" |
| Boards / box | 22 (A or B) |
| Square Feet / box | 11.73 |
| Square Feet / pallet (48 boxes) | 563.04 |

| | |
|------------------------|--------------------------------|
| Weight / box (lbs.) | 26.5 |
| 20' Container Quantity | 22 pallets / 12,386.88 sq. ft. |
| 40' Container Quantity | 33 pallets / 18,580.32 sq. ft. |

(Page 2 of 2)

© 2026 Nydree Flooring, LLC

03/26