

# WEATHERED WOOD


Extruded Porcelain

ARCHITECTURAL  
CERAMICS





COLORS



8x23.6 Blanc\*




2.7x23.6 Blanc\*




14x16.2 Blanc Hex\*



8x23.6 Terra\*




2.7x23.6 Terra\*




14x16.2 Terra Hex\*



8x23.6 Cendra\*




2.7x23.6 Cendra\*




14x16.2 Cendra Hex\*



8x23.6 Negre\*



2.7x23.6 Negre\*



14x16.2 Negre Hex\*

\*Stocked Sizes



































## AVAILABLE SIZES

	FIELD		
	8x23.6	2.7x23.6	14x16.2 HEX
Blanc	M*	M*	M*
Terra	M*	M*	M*
Cendra	M*	M*	M*
Negre	M*	M*	M*

M=Matte finish, \*Stocked Sizes

Lead times for specialty & non-stocked items varies depending on product ordered, quantity, and destination. Please contact ACI to determine the lead time to order samples and material.

## DESCRIPTION

Weathered Wood is an extruded porcelain tile designed to look like an age old floor. The multiple sizes and colors make for a great custom installation.

## INSTALLATION & MAINTENANCE

Weathered Wood may be installed using standard ceramic installation methods and materials, as recommended by the Tile Council of North America (TCNA). An Architectural Ceramics sales representative will advise you on general installation questions.

## TECHNICAL INFORMATION

ORIGIN: SPAIN

AVAILABLE FINISHES: MATTE

TYPE: EXTRUDED PORCELAIN

EDGE: NATURAL

LOOK: WOOD

APPLICATION: FLOOR & WALL

USE: COMMERCIAL & RESIDENTIAL

PACKAGING: PLEASE CONSULT YOUR ACI SALES REP FOR PACKAGING INFORMATION

COLOR VARIATION: V2

THICKNESS: 3/8"

PORCELAIN ENAMEL INSTITUTE SCALE: CLASS IV (BLANC), CLASS III (TERRA), CLASS II (CENDRA & NEGRE)

DYNAMIC COEFFICIENT OF FRICTION: 0.64

BREAKING STRENGTH: COMPLIANT TO ASTM C-648 > 250 LBS

WATER ABSORPTION: 0.30%

STAIN RESISTANCE: YES

FROST RESISTANCE: YES

ENVIRONMENT: 7-8% PRE-CONSUMER RECYCLED CONTENT

## WEBSITE LINKS

[www.architecturalceramics.com/catalogs](http://www.architecturalceramics.com/catalogs)

PLEASE NOTE THIS LINK IS CASE SENSITIVE

## CONTACT INFORMATION:

[www.architecturalceramics.com](http://www.architecturalceramics.com)

1.800.287.1742

For general sales inquiries: [sales@architecturalceramics.com](mailto:sales@architecturalceramics.com)

For commercial & hospitality sample requests: [samples@architecturalceramics.com](mailto:samples@architecturalceramics.com)

Headquarters: 800 E Gude Dr Suite F Rockville, MD 20850